

4200

Polyether polyol

4200 is a sucrose based polyether polyol with a high functionality. It imparts good flowability and properties to a wide range of rigid polyurethane foam systems.

APPLICATIONS

- Appliance insulation, insulated panels, refrigerated transportation vehicles, pour-in-place insulation, block and spray foam.

Typical Properties	Method	Unit	Value
Appearance	QC0-I002-T001	-	Clear to Yellow liquid
Viscosity (@25° C)	QC0-I002-T024	cps	8,000 – 12,000
Hydroxyl Value	QC0-I002-T012	mg KOH/gm	375 – 425
Water content	QC0-I002-T026	%	Max. 0.10
Acid Number	QC0-I002-T002	mg KOH/gm	0.01 – 0.30

STORAGE AND HANDLING

4200 polyol is hygroscopic, and dry nitrogen or low dew point air is recommended for tank padding. Drums should be kept tightly closed to prevent contamination. The recommended storage temperature is 20-25 °C.

TOXICOLOGICAL PROPERTIES

4200 polyol has not been specifically evaluated for its toxicological properties. However, the similarity of the product to others, about which health hazard data is available, provides assurance that it represents minimum hazard. Polyols are low to very low in acute oral toxicity. Because of their low vapor pressure, polyols present no significant inhalation hazard. These materials generally are not irritants to the skin, but can cause mild irritation to the eyes.

NOTICE: The information presented herein, while not guaranteed, is, to the best of our knowledge true and accurate. No warranty or guarantee, express or implied, is made regarding the performance or stability of any product, since the manner of use and conditions of storage and *handling* are beyond our control.