

# 4226

## Polyether polyol

4226 a sucrose based multifunctional polyether polyol with a relatively low hydroxyl value. It imparts good flowability and properties to a wide range of rigid polyurethane foam systems. Its viscosity provides the formulator with considerable flexibility in system formulation.

### APPLICATIONS

- Appliance insulation, insulated panels, pour-in-place insulation
- Refrigerated transportation vehicles
- Block and spray foam.

Typical Properties	Method	Unit	Value
<b>Appearance</b>	QC0-I002-T001	-	Clear, orange yellow – brown liquid
<b>Viscosity (@25° C)</b>	QC0-I002-T025	cps	1,500 – 2,000
<b>Hydroxyl Value</b>	QC0-I002-T012	mg KOH/gm	300 – 320
<b>Water content</b>	QC0-I002-T026	%	Max. 0.10
<b>Acid Number</b>	QC0-I002-T002	mg KOH/gm	0.01 – 0.20
<b>Total K+/Na+</b>	QC0-I002-T021	ppm	Max. 100

### STORAGE AND HANDLING

4226 is hygroscopic, and dry nitrogen or low dew point air is recommended for tank padding. Drums should be kept tightly closed to prevent contamination. The recommended storage temperature is 20-25 °C.

### TOXICOLOGICAL PROPERTIES

4226 has not been specifically evaluated for its toxicological properties. However, the similarity of the product to others, about which health hazard data is available, provides assurance that it represents minimum hazard. Polyols are low to very low in acute oral toxicity. Because of their low vapor pressure, polyols present no significant inhalation hazard. These materials generally are not irritants to the skin, but can cause mild irritation to the eyes.

**NOTICE:** The information presented herein, while not guaranteed, is, to the best of our knowledge true and accurate. No warranty or guarantee, express or implied, is made regarding the performance or stability of any product, since the manner of use and conditions of storage and *handling* are beyond our control.